




TECHNICAL DATA SHEET - CST 0260/02 - 06/06/2016

55 G

(*)				
T	°C	-50 +260		
p	bar			10
V	m/s			10
pH		0 ÷ 14		



(*) Do not use the product to the maximum temperature and pressure associated without consult the manufacturer

Composition

- Extruded graphitized PTFE
- Silicone base lubricant

Features

55G is an extruded pure lubricated and graphitized PTFE, non-sintered. 55G minimize damages on the shafts thanks to its softness. Due to the high PTFE content, it resists chemical attacks over the entire pH range except the strong oxidizers.

Applications

Suitable for acids and alkalis, oils, gas, solvents and steam. It can be used with clean fluids, on centrifugal and plunger pumps, mixers, agitators, on valves, expansion joints and on vacuum pumps.

Size mm	Size inch	kg/box	lbs/box	mt/box	ft/box	mt/kg	ft/lbs
3,0	1/8	1,0	2,2	61,7	203	61,7	91,9
4,0	-	1,0	2,2	34,7	114	34,7	51,7
5,0	3/16	1,0	2,2	22,2	73	22,2	33,1
6,0	-	2,5	5,5	38,6	127	15,4	23,0
6,5	1/4	2,5	5,5	32,9	108	13,1	19,6
8,0	5/16	2,5	5,5	21,7	71	8,7	12,9
9,5	3/8	2,5	5,5	15,4	50	6,2	9,2
10,0	-	2,5	5,5	13,9	46	5,6	8,3
11,0	7/16	2,5	5,5	11,5	38	4,6	6,8
12,0	-	2,5	5,5	9,6	32	3,9	5,7
12,7	1/2	2,5	5,5	8,6	28	3,4	5,1
14,0	9/16	5,0	11,0	14,2	46	2,8	4,2
16,0	5/8	5,0	11,0	10,9	36	2,2	3,2
17,5	11/16	5,0	11,0	9,1	30	1,8	2,7
18,0	-	5,0	11,0	8,6	28	1,7	2,6
19,0	3/4	5,0	11,0	7,7	25	1,5	2,3
22,0	7/8	5,0	11,0	5,7	19	1,1	1,7
25,5	1	5,0	11,0	4,3	14	0,9	1,3

Packaged +/- 10 % in weight